

Transesterification Vitrimers for Photopolymer Additive Manufacturing: Catalyst, Exchange Kinetics, Creep and Reprocessing

Balancing print-time network formation with post-print topology exchange in beta-hydroxy-ester and related vitrimer architectures

Juan Segurola

3Dresyns by Resyner Technologies S.L.

© 2026 Juan Segurola. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-311 · Engineering Review · Version 0.5 · 28 September 2026

Abstract

Photocurable transesterification vitrimers combine a permanent crosslink density with thermally activated topology exchange, enabling stress relaxation, reshaping, repair and reprocessing. The engineering tension is that faster exchange improves reprocessability but can also increase creep or reduce dimensional stability in service. This review focuses on catalyst compatibility with photopolymerisation, exchange kinetics, stress relaxation, thermal stability and the evidence required to distinguish reversible topology rearrangement from degradation.

Keywords: vitrimer; transesterification; photopolymerisation; DLP; stress relaxation; creep; reprocessing

1. Significance and scope

Transesterification vitrimers are important to additive manufacturing because associative ester exchange can permit stress relaxation and reprocessing while preserving network connectivity. The engineering problem is to balance exchange kinetics against creep and service stability, with catalyst state and temperature as explicit variables. Proprietary formulations and machine-specific tuning rules are outside scope.

1.1 Corpus boundary

ER-311 owns transesterification-based photocurable vitrimers and the engineering consequences of associative ester exchange. ER-113 retains cleavable-network chemistry; ER-316 owns urethane/transcarbamoylation exchange; ER-312 owns non-cyclic disulfide exchange.

2. Mechanistic basis

In associative transesterification, an incoming hydroxyl participates in ester exchange while network connectivity is maintained. Exchange rate depends on catalyst identity, hydroxyl/ester availability and temperature. The topology can therefore rearrange above the service regime without a large loss of crosslink density, which is the defining vitrimer concept [1].

3. State variables and process control

Catalyst loading must satisfy two different processes: it should not compromise resin shelf stability or photopolymerisation, yet it must provide useful exchange after printing. The topology-freezing or practical exchange window should be determined from stress relaxation and creep rather than inferred from catalyst concentration. [1,2]

4. Principal failure modes

Excessive exchange at service temperature produces creep and loss of dimensional retention. High-temperature reprocessing can also trigger irreversible side reactions or thermal degradation. Apparent reprocessability based only on reshaping is insufficient if molecular or mechanical properties deteriorate after each cycle [2].

5. Measurement architecture

The minimum evidence set includes photopolymer conversion, DMA, stress relaxation at several temperatures, creep below the intended reprocessing window and repeated reprocessing with mechanical retention. Spectroscopy before and after thermal cycling helps separate exchange from chemical degradation. [1,2]

6. Evidence hierarchy and transfer

DLP-printable thiol-acrylate vitrimers demonstrate that catalyst design can preserve printability while enabling rapid network rearrangement, and subsequent work has questioned the thermal stability margins of transesterification systems during reprocessing [1,2]. Broader dynamic-network studies support the need for topology-state verification [3,4].

7. Qualification architecture

A transesterification-vitrimer qualification package should retain ester/hydroxyl functionality, catalyst identity and state, exchange-temperature history, stress-relaxation kinetics, creep response and property retention after reprocessing. Controls should distinguish exchange-enabled relaxation from thermal softening or degradation. Transfer is justified only when the topology-exchange time scale remains compatible with both service and intended rework conditions.

8. Interpretation and decision logic

Decision logic should balance exchange kinetics against service stability. The network is useful only when stress relaxation becomes fast in the intended reprocessing window while creep and dimensional drift remain acceptably slow at service temperature over the relevant time scale.

Table 1. Qualification matrix for transesterification vitrimers for photopolymer additive manufacturing.

State variable	Minimum evidence	Qualification purpose
Print conversion	Photopolymer conversion	Confirms initial network
Exchange kinetics	Stress relaxation versus temperature	Defines topology mobility
Service creep	Creep below rework window	Checks dimensional stability
Reprocessing	Repeated property retention	Tests circular function

9. Diagnostic interpretation matrix

The diagnostic matrix should distinguish slow exchange, useful associative relaxation, catalyst loss or poisoning, thermal degradation and excessive service creep. Reprocessability should be accepted only when mechanical recovery accompanies evidence that network exchange, rather than simple melting or damage, caused the shape change.

Table 2. Diagnostic interpretation matrix for transesterification-vitrimer behaviour.

Observed deviation	Competing mechanism	Discriminating check
Fast creep	Exchange active in service	Lower-temperature relaxation
Poor rework	Exchange too slow	Temperature/catalyst dependence
Property loss	Thermal degradation	Spectroscopy plus mass/mechanics
Print instability	Catalyst affects cure	Cure kinetics/shelf test

Reprocessing should be demonstrated by more than reshaping a specimen once. At minimum, mass retention, conversion or functional-group state, glass transition or storage-modulus response, and a mechanical property should be compared through repeated cycles. A useful claim distinguishes topology rearrangement from material recovery: a network may be geometrically reprogrammable while still accumulating irreversible chemical damage. Digital-light-processing evidence is therefore strongest when printability, exchange kinetics, service creep and repeated reprocessing are measured on the same chemistry [1,2].

10.1 Reprocessing evidence

For transesterification vitrimers, the central engineering requirement is separation between the service-temperature regime and the topology-rearrangement regime. Stress relaxation that is desirable during repair can become creep during service if the exchange process remains fast under sustained load. The qualification therefore needs isothermal creep and relaxation over a temperature ladder, followed by chemical and mechanical checks after each high-temperature cycle. Thermal stability must be established independently from exchange kinetics because a rapid apparent relaxation can be contaminated by degradation, plasticisation or loss of volatile species [1-4].

9. Service window versus reprocessing window

10. Limitations and evidence gaps

Exchange kinetics depend strongly on catalyst and network chemistry, and the temperature used to demonstrate reshaping may be incompatible with a specific service environment. This review does not treat a single stress-relaxation time as a universal acceptance threshold.

11. Conclusions

Transesterification vitrimers are qualified by the separation between print stability, service stability and reprocessing kinetics. The useful material is not the one with the fastest exchange, but the one whose topology remains effectively frozen in service and predictably mobile during rework.

References

1. Rossegger E, Holler R, Reisinger D, Strasser J, Fleisch M, Griesser T, Schlogl S. Digital light processing 3D printing with thiol-acrylate vitrimers. *Polymer Chemistry*. 2021;12:639-644. doi:10.1039/D0PY01520B.
2. Romano A, Konuray O, Roman F, Calventus Y, Fernandez-Francos X, Roppolo I, Sangermano M. Critical analysis of the thermal stability of transesterification vitrimers for 3D-printing applications based on digital light processing. *Polymer International*. 2024;73(4):280-286. doi:10.1002/pi.6592.
3. Nguyen TD, Nguyen MTN, Lee JS. Dynamic Covalent Bonds in 3D-Printed Polymers: Strategies, Principles, and Applications. *Applied Sciences*. 2025;15(21):11755. doi:10.3390/app152111755.
4. Fang Z, Shi Y, Mu H, Lu R, Wu J, Xie T. 3D printing of dynamic covalent polymer network with on-demand geometric and mechanical reprogrammability. *Nature Communications*. 2023;14:1313. doi:10.1038/s41467-023-37085-9.

Competing interests

The author is Founder, CEO and CTO of 3Dresyns by Resyner Technologies S.L. No comparative product recommendation is made.

Data availability

No new experimental dataset was generated for this review.