

Imine and Hydrazone Dynamic Photopolymer Networks: Water Sensitivity, Exchange, Mechanical Recovery and Chemical Recycling

Engineering reversible C=N chemistry in printed networks where humidity, amine/aldehyde balance and network mobility control service behaviour

Juan Segurola

3Dresyns by Resyner Technologies S.L.

© 2026 Juan Segurola. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-313 · Engineering Review · Version 0.5 · 28 September 2026

Abstract

Imine and hydrazone bonds can exchange or hydrolyse under conditions accessible to polymer processing, giving printed networks reconfigurability, welding and chemical recycling. Their reversibility also creates a service risk because water, pH and residual amine or carbonyl functionality can alter the network after printing. This review links bond chemistry to humidity sensitivity, stress relaxation, mechanical recovery and reprocessing using 4D-printing, biobased DLP and adaptive-surface demonstrations.

Keywords: imine; hydrazone; dynamic covalent network; photopolymerisation; water sensitivity; reprocessing; recycling

1. Significance and scope

Imine and hydrazone dynamic networks are significant because reversible C=N chemistry can enable repair or chemical recycling, but the same exchange chemistry is highly sensitive to water activity, pH and substituent structure. Qualification therefore has to map environmental sensitivity together with exchange rate and mechanical recovery. Proprietary formulations and machine-specific tuning rules are outside scope.

1.1 Corpus boundary

ER-313 owns imine and hydrazone exchange in photocurable/photoprintable networks, including hydrolytic sensitivity and reprocessing. ER-315 owns boronic-esters and ER-312 disulfides. ER-314 owns thermoreversible Diels-Alder networks and is outside the imine/hydrazone exchange problem treated here.

2. Mechanistic basis

Imine exchange can proceed through transimination or hydrolysis/reformation, with kinetics governed by substituent electronics, water activity, catalyst or acid/base state and local mobility. Hydrazones are related but can differ substantially in hydrolytic stability and exchange rate. These mechanisms should not be merged into a single dynamic-bond label. [1]

3. State variables and process control

The relevant material state includes C=N conversion, residual amine/carbonyl content, moisture history and pH. Dry mechanical data cannot by itself establish service stability if the intended environment is humid or aqueous. Reprocessing temperature and pressure should be evaluated against possible hydrolysis or side reactions. [1,2]

4. Principal failure modes

Humidity can plasticise the network and accelerate exchange or hydrolysis, causing dimensional drift. Conversely, a highly glassy network can suppress exchange despite chemically dynamic bonds. Reprocessing may also change stoichiometry if small carbonyl- or amine-containing fragments are lost. [2]

5. Measurement architecture

FTIR or NMR markers of imine state, moisture conditioning, stress relaxation, swelling, repeated tensile recovery and mass balance during reprocessing provide complementary evidence. Chemical recycling claims require recovered-product identification rather than only macroscopic dissolution. [1,2]

6. Evidence hierarchy and transfer

Dynamic-imine 4D-printed systems show permanent shape reconfiguration, and biobased DLP resins demonstrate rapid reprocessability. Recent adaptive-material work extends imine chemistry to post-print surface tuning and welding [1-3], while broader dynamic-network reviews provide comparison with other exchange motifs [4].

7. Qualification architecture

An imine/hydrazone qualification package should retain dynamic-bond identity, water activity, pH or catalyst state, exchange kinetics, mechanical recovery and chemical products after recycling. Dry and humid controls should distinguish bond exchange from hydrolysis-driven loss of connectivity. Transfer is justified only when the environmental window and exchange mechanism remain within the qualified service envelope.

8. Interpretation and decision logic

Decision logic should separate reversible imine or hydrazone exchange from hydrolysis-driven loss of network integrity. Moisture conditioning, chemical-state measurements and mechanical recovery should therefore be interpreted together, with service stability demonstrated at the humidity range relevant to use.

Table 1. Qualification matrix for imine and hydrazone dynamic photopolymer networks.

State variable	Minimum evidence	Qualification purpose
C=N state	Spectroscopic imine/hydrazone marker	Tracks reversible bond
Moisture history	RH/water conditioning	Defines hydrolytic challenge
Exchange kinetics	Stress relaxation	Measures topology dynamics
Reprocessing	Mass and property retention	Tests recoverability

9. Diagnostic interpretation matrix

The diagnostic matrix should distinguish productive transimination or hydrazone exchange, hydrolysis, incomplete reformation, plasticisation and irreversible backbone degradation. Mechanical recovery without chemical-state evidence is insufficient to establish a dynamic-covalent mechanism.

Table 2. Diagnostic interpretation matrix for imine and hydrazone exchange.

Observed deviation	Competing mechanism	Discriminating check
Humidity drift	Hydrolysis/plasticisation	Dry/wet comparison
Slow exchange	Low mobility	DMA plus temperature
Mass loss	Volatile/soluble fragments	Reprocessing mass balance
Weak recovered part	Stoichiometry drift	Spectroscopy and mechanical retest

Chemical recycling is credible only when the recovered material is identified, not merely dissolved or softened. The evidence chain should account for recovered mass, composition or functional-group state, re-formulation or re-crosslinking capability and the properties of a subsequent specimen. For printable systems, the strongest demonstration closes the loop from printed network to triggered deconstruction and back to a qualified network state, while separately documenting any loss caused by hydrolysis, extraction or stoichiometric drift [2-4].

10.1 Chemical recycling and recovered-state qualification

Water cannot be treated as a single environmental variable in imine and hydrazone networks. It can shift reversible-bond equilibria, plasticise the surrounding network and alter mobility and diffusion. Humidity conditioning should therefore be paired with mass uptake, mechanical state and bond-state measurements. A decrease in modulus accompanied by unchanged imine content is different from hydrolytic loss of the dynamic bond, and the recovery trajectory after drying provides an additional discriminator [1-4].

9. Water as reactant, plasticiser and transport medium

10. Limitations and evidence gaps

Imine and hydrazone networks span wide chemical stability ranges. The review therefore does not transfer a humidity threshold or reprocessing temperature across formulations. A system intended for wet service requires direct environmental qualification.

11. Conclusions

Imine/hydrazone printed networks should be qualified through a three-way balance between exchange rate, water sensitivity and network mobility. Reprocessability is valuable only when the same chemistry does not cause unacceptable drift during storage or service.

References

1. Miao J-T, Ge M, Peng S, Zhong J, Li Y, Weng Z, Wu L, Zheng L. Dynamic Imine Bond-Based Shape Memory Polymers with Permanent Shape Reconfigurability for 4D Printing. *ACS Applied Materials & Interfaces*. 2019;11(43):40642-40651. doi:10.1021/acsami.9b14145.
2. Stouten J, Schnelting GHM, Hul J, Sijstermans N, Janssen K, Darikwa T, Ye C, Loos K, Voet VSD, Bernaerts KV. Biobased Photopolymer Resin for 3D Printing Containing Dynamic Imine Bonds for Fast Reprocessability. *ACS Applied Materials & Interfaces*. 2023;15(22):27110-27119. doi:10.1021/acsami.3c01669.
3. Kollwitz M, Balszuweit J, Eisert T, Loza K, Giese M. Designing adaptive materials for 3D-printing via dynamic covalent imine bonds. *Journal of Materials Chemistry C*. 2026. doi:10.1039/D6TC00697C.
4. Nguyen TD, Nguyen MTN, Lee JS. Dynamic Covalent Bonds in 3D-Printed Polymers: Strategies, Principles, and Applications. *Applied Sciences*. 2025;15(21):11755. doi:10.3390/app152111755.

Competing interests

The author is Founder, CEO and CTO of 3Dresyns by Resyner Technologies S.L. No comparative product recommendation is made.

Data availability

No new experimental dataset was generated for this review.