

Reversible Silyl-Ether and Siloxane-Exchange Photopolymer Networks: Trigger Selectivity, Moisture and Dimensional Retention

Dynamic Si-O chemistry, activation selectivity, environmental stability and shape retention

Juan Segurola

3Dresyns by Resynr Technologies S.L.

© 2026 Juan Segurola. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-317 · Engineering Review · Version 0.4 · 27 September 2026

Abstract

Silyl-ether and siloxane exchange reactions provide a family of silicon-oxygen dynamic covalent mechanisms that can combine thermal robustness with post-cure network rearrangement. Their engineering attraction lies in tunable exchange kinetics, chemical selectivity and the possibility of reprocessing or repair without converting the whole network into a low-strength thermoplastic. Their principal risks are equally distinctive: moisture and nucleophile sensitivity, catalyst dependence, possible condensation or hydrolysis, and dimensional drift when exchange becomes active. This review separates silyl-ether exchange from generic siloxane redistribution and treats trigger selectivity as a qualification variable. Evidence from dynamic silyl-ether networks shows that neighbouring amines can substantially accelerate exchange, while recent adaptable-network studies demonstrate reprocessing, repair and stress relaxation in silicon-containing systems. For photocurable implementation, the dynamic silicon-oxygen motif must be compatible with resin storage, photopolymerisation, post-cure and service humidity. A qualification framework is proposed around chemical-state verification, trigger specificity, stress relaxation, creep, moisture cycling, reprocessing, dimensional retention and competing degradation pathways. Keywords: silyl ether; siloxane exchange; covalent adaptable network; photopolymer; stress relaxation; moisture; dimensional retention; reprocessing

1. Significance and scope

Silicon-oxygen linkages span a wide range of chemistries, from robust siloxane backbones to dynamic silyl ethers whose exchange can be accelerated by local catalytic environments. In adaptable polymer networks, this creates an unusual combination of thermal stability and topology rearrangement. This review owns reversible silyl-ether and siloxane-exchange photopolymer networks, with emphasis on trigger selectivity, moisture response and dimensional retention. It does not treat ordinary silicone elastomers as dynamic networks merely because they contain Si-O bonds. Demonstrated exchange under defined conditions is required.

1.1 Corpus boundary

ER-13 retains the umbrella scope for self-healing and interlayer repair. ER-317 is limited to reversible silyl-ether and siloxane exchange as a network mechanism, with emphasis on trigger selectivity, moisture response, stress relaxation and dimensional retention. It does not take ownership of general dynamic-network recycling or other exchange chemistries.

2. Silyl-ether exchange as a dynamic covalent motif

Nishimura and co-workers established silyl ether as a dynamic covalent motif for malleable polymer networks and showed that a neighbouring amino group could accelerate exchange dramatically. Stress relaxation and topology freezing behaviour demonstrated that molecular environment can tune the exchange window without removing the underlying covalent network. For engineering use, this means that nominal bond identity is insufficient. Steric environment, neighbouring-group catalysis, free alcohol or silanol content and catalyst identity can change kinetics. The same silyl-ether group can therefore behave as effectively static in one network and dynamic in another. Exchange should be distinguished from hydrolysis. Loss of a silyl ether in water or under strongly nucleophilic conditions can reduce connectivity without producing a controlled associative rearrangement. Mechanical relaxation accompanied by irreversible mass loss or network degradation is not evidence of useful adaptable-network behaviour. [1,3,4]

3. Siloxane redistribution and network architecture

Siloxane-containing materials can undergo redistribution through several mechanisms, including acid- or base-catalysed equilibration, silanol-mediated condensation and exchange pathways designed into covalent adaptable networks. These mechanisms differ in reversibility, by-products and sensitivity to moisture. [2,4,5]

A photocurable network may combine a permanent carbon-carbon network with dynamic silicon-oxygen crosslinks, or may place the dynamic linkages directly in load-bearing strands. These architectures should not be assumed equivalent. Permanent crosslinks can preserve shape but limit reprocessability; a highly dynamic load-bearing network can improve repair but increase creep. Recent silyl-ether-based adaptable networks and thiol-ene networks show that silicon-oxygen exchange can be incorporated into crosslinked systems with measurable stress relaxation and reprocessing. The qualification question is how much of the observed behaviour comes from designed exchange rather than thermal softening, condensation or phase rearrangement. [2,4,5]

4. Trigger selectivity

A useful dynamic network requires a trigger window that is separated from storage and service. Thermal activation is attractive because it is easy to control, but temperature can also accelerate hydrolysis, oxidation, post-cure and physical ageing. Chemical triggers such as acids, bases, fluoride or nucleophiles may offer faster exchange but raise contamination and compatibility concerns. Trigger selectivity should therefore be measured as a rate ratio: exchange or relaxation under the intended rework condition compared with the same response under storage and service conditions. A large separation is more valuable than the absolute fastest exchange rate. Local photothermal activation, reported in recent adaptable adhesive systems, illustrates a possible route to spatial repair. Such activation should still be tested for thermal gradients, local over-softening and changes in adhesion or dimensions outside the target region. [6]

5. Moisture and environmental stability

Moisture is a central qualification variable because Si-O-C and Si-O-Si chemistry can interact with water through hydrolysis, condensation and surface silanol formation. Depending on formulation, water may accelerate exchange, deactivate a catalyst, plasticise a matrix or irreversibly change connectivity. Humidity studies should track mass, dimensions, modulus, stress relaxation and chemical state before conditioning, at equilibrium and after redrying. Recovery after redrying helps distinguish reversible plasticisation from permanent chemical change, but it does not alone prove that the original network topology has been restored. Applications involving cleaning, sterilisation or outdoor exposure require cycling rather than one-time conditioning. Repeated wet-dry histories can reveal cumulative silanol formation, catalyst migration or interfacial debonding that a single humidity point misses. [1-4]

6. Dimensional retention, repair and reprocessing

Stress relaxation demonstrates network mobility, whereas dimensional retention determines whether that mobility is acceptable in a part. Thin walls, curved beams, holes and unsupported features are more sensitive to topology rearrangement than bulk tensile bars and should be included in print-specific qualification. Repair should be tied to a defined damage mode and property recovery. Reprocessing should report temperature, pressure, dwell time and material yield. If reprocessing requires grinding and hot pressing, the result is distinct from in-place self-healing and should be described as such. For silicon-containing networks used as adhesives or interfaces, recovery of bulk mechanical properties does not guarantee recovery of interfacial adhesion. Surface chemistry and silanol density may change during cycling, so interface-specific tests are required where adhesion is part of the intended function. [1-5]

7. Minimum qualification matrix

The minimum qualification set should separate dynamic exchange, degradation, environment and geometry. It should also include a non-dynamic or exchange-suppressed control where feasible so that thermal annealing and physical ageing are not misassigned to chemistry.

Table 1. Minimum qualification matrix for silyl-ether and siloxane-exchange photopolymer networks.

Domain	Minimum measurement	Primary failure interpretation
Chemical state	Silyl ether/silanol/siloxane state before and after activation and moisture conditioning	Hydrolysis or condensation may mimic useful exchange
Trigger selectivity	Relaxation or exchange rate under service and rework conditions	Insufficient rate separation creates storage or creep risk
Environment	Humidity and solvent cycling with mass, dimensions and mechanical properties	Water can alter both chemistry and morphology
Dynamics	Stress relaxation across a controlled temperature range	Thermal softening alone does not establish topology exchange
Geometry	Feature-level dimensional retention before and after activation	Network mobility may erase intended printed geometry
Reprocessing	Yield, temperature, pressure and retained properties over multiple cycles	Repairability and recyclability must not be inferred from one cycle

8. Interpretation matrix

No single test proves controlled silyl-ether or siloxane exchange. The strongest evidence combines chemical-state measurements, relaxation kinetics, matched controls and recovery of both mechanical and geometric function.

Table 2. Interpretation matrix for common silicon-oxygen network observations.

Observation	Plausible interpretation	Discriminating control
Relaxation accelerates strongly with temperature	Thermally activated exchange or ordinary viscoelastic softening	Chemical-state evidence and exchange-suppressed control
Wet sample heals faster	Water may accelerate exchange or simply plasticise the matrix	Dry-back control and network chemistry after healing
Hot-pressed part retains strength	Reprocessing is feasible, but permanent network damage may remain	Swelling/crosslink analysis and repeated-cycle testing
Local photothermal repair restores adhesion [6]	Dynamic exchange may rebuild the interface	Temperature mapping and untreated-interface control
Shape drifts after humid storage	Exchange, hydrolysis or plasticisation may be active in service	Mass, chemistry and creep measurements under controlled humidity

9. Limitations and evidence gaps

The evidence base for dynamic silyl-ether networks is stronger in bulk adaptable polymers than in vat-photopolymerised systems. Transfer into photocurable resins introduces optical, storage and post-cure constraints that are not captured by bulk-network studies. Siloxane chemistry is mechanistically broad, and published papers may use exchange, redistribution, hydrolysis and condensation terminology differently. Qualification should therefore identify the actual reactive species and by-products rather than relying on a generic Si-O exchange label. Long-term humidity cycling, catalyst migration and dimensional drift under sustained load remain important evidence gaps for printed applications. These variables should be closed before claims of service-stable repairability are made. [1-5]

10. Conclusions

Silyl-ether and siloxane exchange provide credible tools for thermally robust adaptable polymer networks, but the broad label silicon-oxygen dynamic network hides important mechanistic differences. Exchange, hydrolysis, condensation and ordinary thermal softening must be separated experimentally. For photocurable use, the central design problem is trigger selectivity: the network must remain effectively static during storage, printing and service while becoming sufficiently mobile during deliberate repair or reprocessing. Moisture cycling, creep and dimensional metrology are therefore as important as stress relaxation. A useful material is defined not by rapid exchange alone, but by controlled exchange without uncontrolled loss of chemistry, shape or interface performance. [1-5]

References

1. Nishimura Y, Chung J, Muradyan H, Guan Z. Silyl Ether as a Robust and Thermally Stable Dynamic Covalent Motif for Malleable Polymer Design. *Journal of the American Chemical Society*. 2017;139(42):14881-14884. doi:10.1021/jacs.7b08826.
2. Ding Z, Yuan L, Liang G, Gu A. Thermally resistant thermadapt shape memory crosslinked polymers based on silyl ether dynamic covalent linkages for self-folding and self-deployable smart 3D structures. *Journal of Materials Chemistry A*. 2019;7:9736-9747. doi:10.1039/C9TA01147A.
3. Touloukian HE, Vargo AD, El-Zaatari BM. Dynamic Thiol-ene Polymer Networks Enabled by Bifunctional Silyl Ether Exchange. *ACS Applied Polymer Materials*. 2026;8(3):1795-1803. doi:10.1021/acspap.5c03887.
4. Guan R, Wang H, He C, Pan J, Zhao B, Tao L, Yin J. Phase-Locked Dynamic Silyl Ether Metathesis Enabled Mechanically Robust, Self-Healing Polyurethane for Multifunctional Smart Textiles. *Chemistry of Materials*. 2026;38(15):7821-7841. doi:10.1021/acs.chemmater.6c00984.
5. Bijalwan V, Rana S, Yun GJ, Singh KP, Jamil M, Schlögl S. 3D Printing of Covalent Adaptable Networks: Overview, Applications and Future Prospects. *Polymer Reviews*. 2024;64(1):36-79. doi:10.1080/15583724.2023.2227692.
6. Jiang Y, Yang Z, Jin Q, Xu Y, Zhang X, Hakkarainen M. Lignin-derived epoxy covalent adaptable networks with dynamic silyl ether exchange for recyclable glass adhesion and photothermal repair. *Polymer Degradation and Stability*. 2026;251:112228. doi:10.1016/j.polymdegradstab.2026.112228.

Competing interests

The author is Founder, CEO and CTO of 3Dresyns by Resyner Technologies S.L. No comparative product recommendation is made.

Data availability

No new experimental dataset was generated for this review. The analysis is based on the cited literature and the stated engineering scope.