

Phosphorus-Containing Photopolymer Networks: Flame Response, Ion Binding, Hydrolysis and Functional Performance

Treating phosphorus chemistry as a multifunctional design variable rather than a single flame-retardant label

Juan Segurola

3Dresyns by Resyner Technologies S.L.

© 2026 Juan Segurola. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-413 · Engineering Review · Version 0.1 · 7 October 2026

Abstract

Phosphorus-containing monomers and oligomers can alter the thermal decomposition, char formation, ion coordination, polarity and hydrolytic behaviour of photocurable networks. These effects are chemistry-specific: phosphate, phosphonate, phosphinate and phosphine-oxide motifs differ in oxidation state, hydrolysis susceptibility, acidity and interaction with radical cure. This review separates reactive phosphorus incorporation from additive flame retardants and from phosphorus used for ion-binding or surface functionality. It examines how UV-cure conversion, fire response, smoke and residue must be measured separately; why a reduction in one flammability metric cannot be promoted to a universal safety claim; and how water uptake, hydrolysis and leaching can reverse apparent benefits during service. The engineering outcome is a qualification architecture that links phosphorus identity to cure, thermal decomposition, chemical stability and the intended function of the printed or coated article.

Keywords: phosphorus photopolymer; flame retardancy; phosphonate; phosphate; ion binding; hydrolysis; UV curing; qualification

1. Scope: phosphorus is not one function

Phosphorus-bearing photocurable materials are often discussed under flame retardancy, but the same chemical families can also change polarity, adhesion, ion binding, dielectric response and water affinity. Reactive phosphorus-containing acrylates have been incorporated into unsaturated-polyester systems and, separately, UV-cured epoxy-acrylate systems, with formulation-specific changes in combustion behaviour. [1,2] Those demonstrations justify phosphorus as a design variable, not the inference that every phosphorus-containing photopolymer is flame retardant or safer.

2. Chemical identity and oxidation state

Phosphate, phosphonate, phosphinate and phosphine-oxide groups differ in P-C and P-O bonding, acidity, hydrolysis pathways and thermal decomposition. A formulation record should therefore state the phosphorus-bearing structure, whether it is covalently polymerisable, and whether phosphorus remains in the network or can migrate. Weight percent phosphorus alone is insufficient because chemical placement determines both cure compatibility and condensed-phase behaviour.

3. Reactive versus additive phosphorus

A reactive phosphorus monomer is incorporated into the network, whereas an additive flame retardant may remain physically dispersed. Reactive incorporation can reduce migration but may alter crosslink density, viscosity and conversion. Additives can give strong effects at modest formulation changes yet introduce phase separation or leaching. These routes require different extraction and ageing tests. The 2013 studies on phosphorus-containing acrylates are useful because they explicitly link a defined reactive monomer to cured-network behaviour rather than treating phosphorus as an unidentified additive. Jiang et al. explicitly used ultraviolet curing for the epoxy-acrylate system; Bai et al. is cited here for reactive incorporation and combustion behaviour, not as evidence of a UV-curing route. [1,2]

Table 1. Phosphorus roles and evidence

Role	Potential value	Required evidence
Reactive flame-response modifier	Char promotion or altered decomposition	Conversion, declared fire test, smoke/residue, mechanical state
Ion-binding functionality	Cation coordination or uptake	Capacity, selectivity, swelling, kinetics, regeneration
Polarity / adhesion modifier	Interfacial interaction	Surface chemistry, bond strength, ageing
Additive phosphorus phase	High loading without comonomer synthesis	Dispersion, migration/leaching, optical attenuation

4. Flame response must be decomposed into observables

Ignition, heat release, flame spread, smoke, toxic effluent, dripping and residue are separate observables. A change in limiting oxygen index or a small-scale vertical burn result does not establish performance at another test scale. Phosphorus may promote char, modify gas-phase radical chemistry or alter melt behaviour depending on structure and matrix. Qualification therefore requires a declared test method and specimen state, with no transfer from one endpoint to another without evidence.

5. Cure kinetics and conversion

Phosphorus-bearing groups can change resin polarity, absorbance, viscosity and radical environment. The effect on cure may be beneficial, neutral or inhibitory depending on the chromophore and formulation. Conversion should be measured directly, preferably with a method that distinguishes polymerisable unsaturation from phosphorus chemistry. A flame-response improvement observed in an under-

cured network is not a valid material comparison because crosslink density and residual monomer can independently alter decomposition and mechanical response.

6. Ion binding and electrochemical relevance

Phosphate and phosphonate groups can coordinate cations and increase local polarity, which can be useful in ion-conducting or adsorption systems. That function creates a different qualification problem from flame retardancy: ion capacity, selectivity, swelling, conductivity and regeneration become primary. The same binding that improves uptake can also increase water absorption or plasticisation. Function must therefore be measured under the ionic strength, pH and temperature of intended service.

7. Hydrolysis, water uptake and leaching

P-O-C containing motifs can be more hydrolysis-sensitive than P-C-rich structures, and hydrophilic phosphorus groups can increase water uptake. Long-term service should be tested by mass change, dimensional change, spectroscopy and leachate analysis rather than by dry-state properties alone. Hydrolysis can simultaneously change mechanical properties and release acidic or ionic species, so a stable initial cure is not evidence of chemical stability.

8. Processing and VPP transfer

For VPP, phosphorus chemistry interacts with viscosity, optical attenuation, inhibitor level and photoinitiator spectrum. Filled intumescent systems may be particularly difficult to transfer because scattering and sedimentation alter exposure. Reactive molecular phosphorus routes can avoid particulate settling but still modify cure depth. Printer qualification must therefore include dose-depth response, dimensional coupons and post-cure state before fire or ion-binding performance is interpreted.

Table 2. Failure interpretation

Observation	Possible causes	Discriminating test
Lower heat release but brittle part	Char-forming chemistry or lower conversion	Conversion plus mechanical/thermal analysis
Property loss after water exposure	Hydrolysis, plasticisation, leaching	Mass change, spectroscopy, leachate analysis
Poor VPP cure depth	Absorption/scattering or kinetic inhibition	Spectral absorbance and dose-depth measurement

9. Failure diagnosis

A failed phosphorus-containing system can present as incomplete cure, brittle char-forming network, excessive swelling, leaching, haze, or unstable ion uptake. These failures are mechanistically different. The diagnostic sequence should first confirm composition and conversion, then separate thermal decomposition from mass transport and water-driven change. Fire tests alone cannot diagnose cure defects, and water-uptake tests alone cannot establish phosphorus retention.

10. Qualification decision boundary

A phosphorus-containing photopolymer should be released only against the function actually demonstrated. Flame-response claims require declared fire-test evidence; ion-binding claims require equilibrium and kinetic measurements; hydrolytic stability requires ageing and chemical analysis. A single phosphorus concentration cannot serve as a universal acceptance variable. The boundary is the intersection of cure state, chemical stability and the intended functional endpoint.

11. Evidence gaps

Much of the phosphorus UV-curing literature predates contemporary VPP workflows and focuses on coatings or bulk-cured resins, while broader reviews confirm the distinction between reactive and additive phosphorus strategies. [3,4] Direct studies combining printer processability, conversion, fire response, smoke, hydrolysis and leaching remain limited. Evidence for ion-binding in printed phosphorus-rich networks is even more fragmented. These gaps support cautious transfer of chemistry principles but not universal print-performance claims.

12. Research priorities

Useful work would compare matched reactive phosphorus motifs at equal network conversion, report phosphorus retention after ageing, and combine microcalorimetry or standardised fire tests with smoke and residue characterisation. For ion-binding materials, uptake and conductivity should be tested through repeated wet-dry cycles. For VPP, optical attenuation and working-curve shifts should be mapped as phosphorus chemistry is varied.

13. Measurement architecture for phosphorus networks

The preferred evidence chain starts with phosphorus identity and retained concentration, then measures conversion, thermal decomposition and functional output on the same formulation series. Solid-state or solution NMR, elemental analysis or mass spectrometry can confirm the phosphorus-bearing structure where appropriate. Photo-DSC or FTIR establishes cure behaviour. Fire testing then needs a declared scale, specimen thickness and conditioning history, while water exposure and leachate analysis establish whether the functional chemistry remains in the network. No single technique closes the chain.

14. Coupled thermal-mechanical interpretation

A phosphorus chemistry that increases char yield can also change glass transition, crosslink density or brittleness. Those changes matter because a stiffer or more brittle article can fail mechanically before a fire-response benefit becomes relevant. Thermal analysis should therefore be paired with mechanical testing before and after ageing. If a formulation is intended for electrical or ion-binding use, the same thermal decomposition pathway can influence dielectric loss, conductivity or interfacial stability and should be treated as a coupled material-state problem.

15. Discriminating experiment set

A strong comparison uses a phosphorus-free control and at least two chemically distinct phosphorus-bearing formulations adjusted to similar initial conversion. Fire response, residue, smoke-related observables where available, water uptake and mechanical state are then measured after identical conditioning. For VPP transfer, working-curve and feature-fidelity data are added. This design allows a change in flame response to be separated from under-cure, filler scattering or a simple increase in network stiffness.

16. Engineering conclusion

Phosphorus can provide useful flame-response, ion-binding and interfacial functions in photocurable networks, but those functions arise from specific chemical motifs rather than from phosphorus concentration alone. Engineering qualification requires a declared reactive or additive route, controlled cure state, hydrolytic stability and an application-specific functional test. Claims should remain bounded to the measured endpoint and test scale; the phrase phosphorus-containing is a composition descriptor, not a performance certification.

References

1. Bai ZM, Song L, Hu Y, Yuen RKK. Preparation, Flame Retardancy, and Thermal Degradation of Unsaturated Polyester Resin Modified with a Novel Phosphorus Containing Acrylate. *Industrial & Engineering Chemistry Research*. 2013;52(36):12855-12864. doi:10.1021/ie401662x.
2. Jiang S, Shi Y, Qian X, Zhou K, Xu H, Lo SM, Gui Z, Hu Y. Synthesis of a Novel Phosphorus- and Nitrogen-Containing Acrylate and Its Performance as an Intumescent Flame Retardant for Epoxy Acrylate. *Industrial & Engineering Chemistry Research*. 2013;52(49):17442-17450. doi:10.1021/ie4028439.
3. Singh I, Sivaramakrishna A. Phosphorus-Based Polymeric Flame Retardants - Recent Advances and Perspectives. *ChemistrySelect*. 2024;9:e202401485. doi:10.1002/slct.202401485.
4. Huo S, Song P, Yu B, Ran S, Chevali VS, Liu L, Fang Z, Wang H. Phosphorus-containing flame retardant epoxy thermosets: Recent advances and future perspectives. *Progress in Polymer Science*. 2021;114:101366. doi:10.1016/j.progpolymsci.2021.101366.

Competing interests

The author is Founder, CEO and CTO of 3Dresyns by Resyner Technologies S.L.; ER-413 contains no comparative product recommendation.

Data availability

ER-413 is a literature-based engineering review; no new experimental dataset was generated.