

Microgravity Effects on Photopolymer Cure: Convection, Bubbles, Sedimentation, Interfaces and Network Uniformity

Separating reaction kinetics from transport phenomena when photopolymerisation occurs without terrestrial buoyancy

Juan Segurola

3Dresyns by Resyner Technologies S.L.

© 2026 Juan Segurola. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-444 · Engineering Review · Version 0.1 · 8 October 2026

Abstract

Microgravity modifies photopolymerisation primarily by changing transport and boundary conditions around a reaction that still depends on light, chemistry and heat. Natural convection is suppressed, sedimentation and buoyant bubble migration are reduced, capillary forces gain relative importance and reaction heat can accumulate locally. Historical microgravity polymerisation studies and recent in-space photopolymer experiments show that these effects can either reduce gravity-driven gradients or create new thermal and interfacial defects. This review defines the variables required to distinguish chemical kinetics from gravity-dependent transport and to qualify network uniformity in photocurable systems.

Keywords: microgravity; photopolymerisation; convection; bubbles; sedimentation; heat transfer; interfaces; network uniformity; cure kinetics

1. Significance and scope

Photopolymer chemistry does not stop obeying kinetics in microgravity, but the transport fields around the reaction change. Historical polymerisation research demonstrated gravity-sensitive convection and structure formation, while recent in-space work links suppressed natural convection to thermal defects in photocurable resins [1-3].

ER-443 owns machine containment, optics, motion and release. This review owns the material-physics question: how the absence of terrestrial buoyancy changes heat, gas, particles and interfaces during cure.

2. Microgravity transport and thermal accumulation

On Earth, density gradients created by temperature or conversion can drive natural convection. In microgravity that transport weakens, so diffusion and conduction carry a larger share of heat and mass transport [2,3].

Removing convection can improve some compositional gradients while simultaneously increasing local thermal accumulation. “More uniform” therefore cannot be assumed from microgravity alone; the relevant field must be measured.

Recent photopolymer experiments under microgravity show that local heat buildup can become a first-order defect mechanism. Formulation absorption, reaction rate, sample dimensions and thermal contact determine whether the cure remains below a damage or blistering threshold [2].

3. Heat transfer can dominate cure uniformity

Kinetic interpretation should separate conversion from temperature. A faster or deeper cure under one gravity condition may reflect a different thermal history rather than an intrinsic change in photochemical reaction constants. Thermal modelling of in-space photopolymer fabrication makes this heat-transfer coupling explicit [3].

Gas bubbles respond to pressure and surface tension as well as gravity. Reduced buoyancy means bubbles may not rise out of the exposure region, while reduced pressure can expand trapped gas dramatically [1].

4. Bubbles and interfaces no longer behave terrestrially

A bubble can remain as an optical lens, shadow, void nucleus or heat-transfer discontinuity. Bubble size distribution and location should be recorded before, during and after cure rather than collapsed into a final porosity value.

Free surfaces and liquid-solid interfaces become more capillary-dominated in microgravity. Contact angle, surface energy and wetting history can determine interface curvature and thickness, which in turn changes local optical path length and cure.

Filled photopolymers add a second transport problem. Reduced sedimentation may help retain particles in suspension, but aggregation, diffusion-limited rearrangement and exposure-induced viscosity changes can still create spatially varying filler states.

Optical attenuation couples to that particle field. A uniform particle concentration before launch does not guarantee a uniform state after storage, acceleration transients and cure.

5. Filled-system transport and device-level verification

Network uniformity should be assessed across position using conversion, swelling, modulus, spectroscopy or another spatially resolved measure. Bulk average conversion can hide a hot core, inhibited surface or particle-rich region.

Device-level verification should deliberately vary orientation and acceleration history when the process will experience launch, coast and manoeuvre phases. The test question is whether the material state remains within specification across those transitions.

A terrestrial control and a reduced-gravity specimen should share formulation, dose definition, thermal boundary and geometry whenever the gravity effect itself is being attributed. Otherwise multiple changed variables prevent mechanistic interpretation.

Axis	Measurement	Failure mode
Thermal transport	local temperature and boundary condition	microgravity effect assigned to chemistry alone
Gas phase	bubble size, location, pressure history	final porosity hides bubble dynamics
Particles	dispersion and spatial loading	absence of sedimentation assumed uniform
Interfaces	wetting and interface geometry	terrestrial free surface assumed
Network state	spatial conversion/property map	bulk average treated as uniformity

Table 1. Domain-specific qualification matrix for microgravity effects on photopolymer cure.

6. Transfer limits and minimum reporting dataset

Microgravity benefits should not be generalized from one resin chemistry. Absorptivity, viscosity, oxygen sensitivity, filler loading and reaction enthalpy all change the relative importance of transport mechanisms.

Report gravity/acceleration history, pressure, geometry, thermal boundary, resin state, gas content, particle state, optical dose, temperature and spatial conversion or property measurements.

Where uniformity is claimed, define the spatial resolution and acceptance range. Distinguish reaction kinetics from heat- and mass-transfer effects explicitly.

7. Minimum qualification framework

A minimum cure-physics programme should measure conversion or an equivalent cure metric together with temperature, interface geometry and gas state under matched gravity conditions. Bubble nucleation, migration and persistence should be reported explicitly because reduced buoyancy can convert a transient defect into a trapped optical or mechanical discontinuity.

Where particles or fillers are present, concentration profiles before and after exposure should be measured rather than inferred from terrestrial sedimentation behaviour. Replicates should distinguish stochastic bubble/interface events from systematic changes in reaction or transport, and terrestrial controls should match thermal boundary conditions as closely as possible.

8. Engineering conclusions

Microgravity does not create a new photochemistry, but it changes the transport processes surrounding photopolymerisation. The engineering requirement is therefore to identify which cure outcomes are reaction-limited and which are convection-, buoyancy-, sedimentation- or interface-limited before claiming network uniformity in reduced gravity.

References

- [1] V. Briskman, K. G. Kostarev, V. Levto, T. Lyubimova, “Polymerization under different gravity conditions,” *Acta Astronautica* 39 (1996) 395-402. [https://doi.org/10.1016/S0094-5765\(96\)00068-9](https://doi.org/10.1016/S0094-5765(96)00068-9)
- [2] M. Kringer, A. Titz, P. Maier, F. Schill, J. Pimpi, L. Hoffman, U. Lafont, P. Reiss, M. Pietras, “Effects of microgravity and reduced atmospheric pressure on manufacturing photopolymer specimens,” *Acta Astronautica* 218 (2024) 314-325. <https://doi.org/10.1016/j.actaastro.2024.01.033>
- [3] J. Ericson, D. Widerker, E. Stibbe, M. Elgarisi, Y. Katzman, O. Luria, K. Gommed, A. Razin, A. A. Hari, I. Gabay, V. Frumkin, H. Abu Hamad, E. Segal, Y. Amouyal, T. Szobody, R. Ticknor, E. Balaban, M. Bercovici, “Modeling the thermal behavior of photopolymers for in-space fabrication,” *npj Microgravity* 12 (2026) 75. <https://doi.org/10.1038/s41526-026-00612-1>

Competing interest

Juan Segurola is founder, CEO and CTO of 3Dresyns by Resyner Technologies S.L., which develops and commercialises photopolymer materials and related additive-manufacturing technologies. This review is an engineering analysis and does not constitute a product-performance claim or a device qualification.