

Membrane, Adsorptive and Hybrid Purification of Used Photopolymer Wash Solvents: Selectivity, Fouling and Quality Control

Engineering solvent recovery around resin contamination, azeotropy, separation selectivity and reuse acceptance

Juan Seguro

3Dresyns by Resyner Technologies S.L.

© 2026 Juan Seguro. All Rights Reserved.

Correspondence: info@3Dresyns.com · www.3Dresyns.com

ER-458 · Engineering Review · Version 0.1 · 8 October 2026

Abstract

Wash solvents from vat-photopolymer workflows accumulate uncured resin, oligomers, pigments, particles and water while the solvent itself evaporates and changes composition. Recovery therefore requires selective removal of contaminants and evidence that the regenerated solvent remains fit for washing. This review defines a qualification framework for membrane, adsorptive and hybrid purification of used photopolymer wash solvents, using isopropanol as the principal example. It addresses contaminant loading, prefiltration, distillation or membrane separation, adsorption, fouling, solvent loss and reuse quality.

Keywords: wash solvent; isopropanol; photopolymer; solvent recovery; membrane; adsorption; distillation; fouling; purification

1. Significance and scope

Vat-photopolymer post-processing commonly transfers uncured resin into a volatile organic wash solvent. Once used, that liquid is not simply dilute resin: it can contain water, oligomers, pigments, particles and degradation products with very different separation behaviour.

This review owns purification and reuse of used wash solvent. It does not prescribe a single solvent or purification train; it defines the evidence needed to claim that regenerated solvent is fit for controlled washing.

2. Used wash solvent is a changing mixture

Characterisation should begin with solvent fraction, water, dissolved organics, suspended solids, colour and any process-specific contaminants. A conductivity or density reading can be useful only after correlation with actual contamination.

Isopropanol-recovery studies outside additive manufacturing show that contaminated solvent streams can require integrated separation rather than one unit operation. Air stripping, condensation and activated-carbon polishing have been combined to recover IPA from complex waste solvent [1].

Wash-solvent contamination should be described in terms of both dissolved and suspended fractions. Settling can temporarily improve clarity while leaving a dissolved load that still changes washing power and evaporation residue.

Water management should be explicit because hygroscopic solvent handling and repeated washing can change the feed independently of resin loading. A purification route that removes organics while allowing water to accumulate may progressively alter washing power and drying behaviour.

3. Separation route must match contaminant class

Distillation is effective when volatility differences dominate, but water/IPA azeotropy and nonvolatile resin residues change energy and purity requirements. Resin-rich bottoms also require controlled disposal or secondary recovery.

Membrane routes can separate solvent/water systems without full vaporisation, but performance depends on selectivity, flux and feed composition. Modern membrane-distillation work shows that IPA recovery can be treated as a constrained optimisation problem rather than a single operating point [2].

4. Membranes trade selectivity against fouling

Used photopolymer solvent introduces a fouling problem absent from clean binary feeds. Oligomers and pigments can adsorb on or plasticise membranes, so flux stability and cleaning recovery should be measured over realistic load cycles.

Prefiltration can protect membranes and columns from particles but does not remove dissolved resin. Filter mass gain should not be mistaken for total contaminant removal.

Adsorption is useful for residual organics or vapour capture and can be integrated with condensation or distillation. Carbon-based recovery systems illustrate the importance of regeneration and breakthrough behaviour [1].

Purification equipment should be challenged with the highest credible contaminant load, not only a lightly used bath. Breakthrough, membrane fouling and distillation residue behaviour often become visible only near the upper operating range.

Cleaning validation belongs to membrane and adsorbent qualification. Restored flux after cleaning does not by itself prove chemical cleanliness; extractables, desorbed contaminants or cleaning-agent carryover can enter the recovered solvent and later redeposit on printed surfaces.

5. Adsorption and hybrids can polish recovered solvent

Hybrid trains may combine settling, filtration, distillation, pervaporation, membrane distillation and adsorption. The sequence should be justified by contaminant class and the quality target for solvent reuse.

Solvent loss during purification belongs in the mass balance. A high-purity product obtained at low recovery may not improve operating consumption or environmental burden.

Recovered solvent should be released by properties linked to washing: solvent concentration, water content, residue after evaporation, colour/absorbance and contamination that can redeposit on parts.

Axis	Measurement	Failure mode
Feed	solvent, water, dissolved and suspended load	used solvent treated as binary mixture
Separation	route, selectivity, recovery	purity reported without yield
Fouling	flux/breakthrough and cleaning	fresh separator treated as steady state
Mass balance	product, reject and solvent loss	discarded residue omitted
Reuse	wash performance and redeposition	chemical purity treated as functional release

Table 1. Domain-specific qualification matrix for purification and reuse of photopolymer wash solvents.

6. Device-level verification by wash performance

Device-level verification should wash representative printed parts with virgin and recovered solvent under identical agitation, time and loading. Measure residual uncured resin, surface contamination and downstream cure or appearance.

Reuse cycles should be tracked because contaminants can accumulate below the purge threshold. A solvent that passes one regeneration can drift after repeated recycling if the purification train selectively leaves one impurity class.

Pervaporation studies of IPA/water mixtures demonstrate that membrane composition and operating conditions govern flux-selectivity trade-offs [3]; analogous qualification is required before applying membranes to resin-contaminated solvent.

Device-level qualification should define a reuse endpoint over repeated cycles. A single regenerated batch demonstrates feasibility, whereas a controlled sequence of contamination, purification and reuse is needed to establish steady-state purge requirements and contaminant accumulation.

7. Minimum qualification framework

Report feed composition, solvent identity, contamination load, pretreatment, separation method, temperature/pressure, membrane or adsorbent identity, throughput and regeneration method.

Report recovered-solvent yield and composition, reject streams, fouling or breakthrough behaviour, energy or utility inputs, and wash-performance acceptance tests.

8. Engineering conclusions

Wash-solvent recovery should be qualified by both separation performance and reuse function. The correct endpoint is not a clear distillate or permeate, but a solvent lot that performs a defined photopolymer washing task without transferring hidden contamination.

References

- [1] S. H. Lin, C. S. Wang, "Recovery of isopropyl alcohol from waste solvent of a semiconductor plant," *Journal of Hazardous Materials* 106 (2004) 161-168. <https://doi.org/10.1016/j.jhazmat.2003.11.012>
- [2] J. Park, M. Cheon, S. Park, J. H. Lee, D.-Y. Koh, "Sustainable Isopropyl Alcohol Recovery via Data-Driven, Active-Learning Optimization of Vacuum Membrane Distillation," *ACS Sustainable Chemistry & Engineering* 12 (2024) 11510-11519. <https://doi.org/10.1021/acssuschemeng.4c01285>
- [3] N. D. Hilmioglu, S. Tulbentci, "Pervaporative separation of isopropyl alcohol/water mixtures: effects of the operation conditions," *Desalination and Water Treatment* 48 (2012) 191-198. <https://doi.org/10.1080/19443994.2012.698812>

Competing interest

Juan Segurola is founder, CEO and CTO of 3Dresyns by Resynr Technologies S.L., which develops and commercialises photopolymer materials and related additive-manufacturing technologies. This review is an engineering analysis and does not constitute a product-performance claim or a device qualification.